

### AMENDMENTS TO THE CLAIMS

Please amend claims 3, 4 and 5 and add new claims 8-14 as follows:

#### Listing of Claims

**Claim 1 (Original):** An anti-microbial, curable silicone rubber composition comprising in at least a portion of the exposed surface of said composition an organic matrix containing homogeneously dispersed particles of metallic silver having a particle size in the range of 1 to 50 nm (silver nanoparticles) in an amount providing on the surface of said composition an anti-microbially effective but less than cytotoxic silver concentration.

**Claim 2 (Original):** The silicone rubber composition according to claim 1, characterized by comprising said silver nanoparticles in an amount providing a silver concentration of from more than 1 nmol/l to less than 1  $\mu$ mol/l on at least a portion of the surface of said composition.

**Claim 3 (Currently amended):** The silicone rubber composition according to claim 2, characterized in that said organic matrix comprises said silver nanoparticles in an amount of 1 to 2000 ppm, ~~preferably 5 to 1 000 ppm and more preferably 10 to 250 ppm.~~

**Claim 4 (Currently amended):** The silicone rubber composition according to claim 3, characterized by comprising silver nanoparticles having a particle size of 2 to 20 nm ~~preferably 5 to 10 nm.~~

**Claim 5 (Currently amended):** The silicone rubber composition according to claim 1, characterized in that said ~~fluid~~ organic matrix comprises an organic fluid wherein said silver nanoparticles are dispersed.

**Claim 6 (Original):** The silicone rubber composition according to claim 5, characterized in that said viscous organic fluid comprises an aliphatic or aromatic hydrocarbon, a mineral oil, petrolatum, glycerol, a fatty alcohol, polypropylene glycol, an animal and/or vegetable oil or fat, or a silicone oil.

**Claim 7 (Original):** A method for manufacturing a curable, anti-microbial silicone rubber

composition comprising the steps of:

- providing a curable silicone rubber composition in a configuration ready for mixing
- providing a liquid organic matrix comprising metallic silver having a particle size in the range of 1 to 50 nm
- mixing said liquid organic matrix into said silicone rubber composition
- optionally curing the mixture of said composition with said organic matrix

**Claim 8 (New):** The silicone rubber composition according to claim 3, characterized by comprising silver nanoparticles having a particle size of 5 to 10 nm.

**Claim 9 (New):** The silicone rubber composition according to claim 2, characterized in that said organic matrix comprises said silver nanoparticles in an amount of 5 to 1000 ppm.

**Claim 10 (New):** The silicone rubber composition according to claim 9, characterized by comprising silver nanoparticles having a particle size of 2 to 20 nm.

**Claim 11 (New):** The silicone rubber composition according to claim 9, characterized by comprising silver nanoparticles having a particle size of 5 to 10 nm.

**Claim 12 (New):** The silicone rubber composition according to claim 2, characterized in that said organic matrix comprises said silver nanoparticles in an amount of 10 to 250 ppm.

**Claim 13 (New):** The silicone rubber composition according to claim 12, characterized by comprising silver nanoparticles having a particle size of 2 to 20 nm.

**Claim 14 (New):** The silicone rubber composition according to claim 12, characterized by comprising silver nanoparticles having a particle size of 5 to 10 nm.